

Codice: 7F6332

## Plamur Finisher Light/Mdf

### TWO-COMPONENT EPOXY FILLER FOR SURFACE LEVELLING

Two-component epoxy filler for high thickness levelling on small and large surfaces of boats. Used in two-component coating systems. Available in the Light or MDF version according to specific requirements.



#### Technical Characteristics

|  |                            |
|--|----------------------------|
| <b>Paint Type</b>                      | Two components             |
| <b>Binder type A</b>                   | Epoxy modified             |
| <b>Binder type B</b>                   | Amminic                    |
| <b>Specific gravity kg/lit (±0,05)</b> | 1,540 (A) - 0,980 (B)      |
| <b>Solids content (volume) ±2</b>      | 100%                       |
| <b>Viscosity Ford ø 8 at 20°C ±2</b>   | Tixotropico (A+B)          |
| <b>Shelf life (+10+30°C)</b>           | 12 months in airtight cans |

#### Application Data

|   |                                 |
|---|---------------------------------|
| <b>Application</b>                        | Spatula                         |
| <b>Mixing ratio A+B by volume</b>         | 1 Part.Sol.A with 1 Part.Sol.B  |
| <b>Temperature Pot Life</b>               | 20°C                            |
| <b>Sandable</b>                           | After 24 HOURS                  |
| <b>Touch dry</b>                          | 6-8 h ( 20°C)                   |
| <b>Spatula</b>                            | Ready to use                    |
| <b>Recoat time</b>                        | Minimum 24-36 h (20°C)          |
| <b>Application temperature</b>            | Between +10 C et +40 C          |
| <b>Relevant humidity</b>                  | Less than 80%                   |
| <b>Dry film thickness advised</b>         | 300 microns by hands            |
| <b>Theoret. coverage m<sup>2</sup>/Lt</b> | 4 to a thickness of 250 microns |

### SURFACE PREPARATION AND APPLICATION

#### Steel.

Sandblasting according to SA 2,5. Apply a first coat of EPOFOND AM-9 and let dry. Sandpaper and apply EPOXY LIGHT FILLER NS and let dry for 24-48 hours. Apply PLAMUR FINISHER LIGHT/MDF to obtain a smoother surface. Sandpaper and follow up with the recommended coating system.

#### Alluminium-Fibreglass-Cement-And Light Alloys.

Remove mechanically any oxidized layer from the substrate. Remove dust and degrease with THINNER 765. Apply one coat of EPOFOND AM-9 primer. After 12 hours sandpaper and apply EPOXY LIGHT FILLER NS and let dry for 24-48 hours. Apply PLAMUR FINISHER LIGHT/MDF to obtain a smoother surface. Sandpaper and follow up with the recommended coating system.

NB: This product is part of the Skipper's Line of Marine Coatings. For further application details please also see the "Indicative Coating Systems information" available on demand for Wood, Steel, Aluminium and Fibreglass boats. When in doubt contact for advise.

Codice: 7F6332

# Plamur Finisher Light/Mdf

## Colors



Colore: GRIGIO  
Cod. Colore: 7F6332

## Listino

| Formati Disponibili | Codice      | Descrizione                 | Confezione |
|---------------------|-------------|-----------------------------|------------|
| 5L                  | 7F597300500 | Plamur Finisher light Sol.A | 0.50 lt    |
| 1L                  | 7F597302500 | Plamur Finisher light Sol.A | 2.50 lt    |
|                     | 7F633200500 | Plamur Finisher MDF Sol.A   | 0.50 lt    |
|                     | 7F633202500 | Plamur Finisher MDF Sol.A   | 2.50 lt    |
|                     | 8Z597400500 | Plamur Finisher light Sol.B | 0.50 lt    |
|                     | 8Z597402500 | Plamur Finisher light Sol.B | 2.50 lt    |
|                     | 8Z633300500 | Plamur Finisher MDF sol.B   | 0.50 lt    |
|                     | 8Z633302500 | Plamur Finisher MDF sol.B   | 2.50 lt    |

## SAFETY PRECAUTIONS

Before starting paint application attention should be paid to the symbols of risk specified on the label of each can. Please carefully read all the safety precautions advised on the label, or in the safety data sheet available on request at [laboratorio@aemmecolori.it](mailto:laboratorio@aemmecolori.it)

## NOTES

This information is provided to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, this information does not constitute any kind of implied warranties; in that sense the supplying company accepts from now responsibility that can be connected to an abnormal use of the products. The Engineering Department at your location is available for any questions related to the use of our products. The percentages of dilution and the drying time are to be considered only indicative, in relation to a temperature of 20 ° C and are therefore subject to change with the change of temperature, in the presence of particular weather conditions or application determining factors at the time of 'application.