

Codice: 2U3900

Solver Primer



CHLORINATED-RUBBER BASED ONE-COMPONENT INTERMEDIATE UNDERCOAT

Primer and intermediate undercoat based on chlorinated rubber, formulated with aluminium and rust inhibitor pigments. Applied as a keying coating between old and new antifoulings or in anticorrosive coating systems. Provides outstanding resistance in marine and industrial environment. Recommended on metal structures exposed in marine environment.

Techical Characteristics		Application Data	
Paint Type	One component	Application	Brush-Roller-Spray
Binder type A	Chlorinated-alkyd	Brush-Roller	10-25% Diluente 400
Specific gravity kg/lt (±0,05)	1,250	Spray	15-30% Diluente 400
Solids content (volume) ±2	30%	Touch dry	2-3 h (20°C)
Viscosity Ford ø 8 at 20°C ±2	20"	Recoat time	Minimum 6 h (20°)
Shelf life (+10+30°C)	18 months in airtight cans	Application temperature	Between +10 C et +40 C
		Relevant humidity	Less than 80%
		Dry film thickness advised	60-70 microns by hand
		Theoret. coverage m2/Lt	4-6

SURFACE PREPARATION AND APPLICATION

Steel.

Apply one coat of EPOZINC 1C onto sandblasted iron and let dry for 12-24 hours. If sandblasting is not possible the substrate should be mechanically brought to bare steel. Clean the surface and apply one primer coat of CROMOMINIO-AT and let dry for 24 hours. Apply 1-2 coats of SOLVER PRIMER allowing 24 hours between coats. Overcoat with recommended finish.

Boat bottom.

Apply 2-3 coats of SOLVER PRIMER on a suitable basecoat allowing 24 hours between coats and overcoat with 2-3 coats of antifouling paint.

Boat topsides.


Apply 2 coats of SOLVER PRIMER on a suitable basecoat allowing 24 hours between coats and overcoat with 2 coats of recommended topcoat enamel.

NB: This product is part of the Skipper's Line of Marine Coatings. For further application details please also see the "Indicative Coating Systems information" available on demand for Wood, Steel, Aluminium and Fibreglass boats. When in doubt contact for advise.

Codice: 2U3900

Solver Primer

Colors



Colore: Giallo
Cod. Colore: 2U3900

Listino

Formati Disponibili			Codice	Descrizione	Confezione
18L	2.5L	0.75L	2U390000750	Solver primer	0.75 lt
			2U390002500	Solver primer	2.50 lt
			2U390018000	Solver primer	18.00 lt

SAFETY PRECAUTIONS

Before starting paint application attention should be paid to the symbols of risk specified on the label of each can. Please carefully read all the safety precautions advised on the label, or in the safety data sheet available on request at laboratorio@aemmecolori.it

NOTES

This information is provided to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, this information does not constitute any kind of implied warranties; in that sense the supplying company accepts from now responsibility that can be connected to an abnormal use of the products. The Engineering Department at your location is available for any questions related to the use of our products. The percentages of dilution and the drying time are to be considered only indicative, in relation to a temperature of 20 ° C and are therefore subject to change with the change of temperature, in the presence of particular weather conditions or application determining factors at the time of application.