

Codice: 7K6015

Stripcarena



Stripcarena is a water-thinable antifouling remover formulated with non-toxic compounds

Stripcarena is a water-thinable antifouling remover formulated with non-toxic compounds. Stripcarena can remove old antifouling from fibreglass without impairing the gel coat. The product is ready for use and is applied at the thickness required to penetrate the old antifouling. Once applied should be left to work for approx. 1-2 hours. Remove then the old paint by means of a scraper or using a water jet. If necessary repeat the process.

Technical Characteristics

Paint Type	One component
Binder type A	Synthetic
Specific gravity kg/lit (±0,05)	1.04
Viscosity Ford ρ 8 at 20°C ±2	Tixotropico
Shelf life (+10+30°C)	18 months in airtight cans

Application Data

Curing time	1-3 hours
Application temperature	Between +10 C et +40 C
Relevant humidity	Less than 80%
Theoret. coverage m2/Lt	2-3 seconds the thickness


SURFACE PREPARATION AND APPLICATION

Fibreglass coated with antifouling.

The product is applied by brush, preferably at a high thickness depending however on the antifouling layer to be removed. Once applied let stand for 1-2 hours. Remove then by scraper or by using a water-cleaner equipment. In case of high thickness of antifouling to be removed it may be necessary to repeat the process. When the paint has been finally removed, rinse the surface very well with water using a synthetic or vegetal wirebrush.

NB: This product is part of the Skipper's Line of Marine Coatings. For further application details please also see the "Indicative Coating Systems information" available on demand for Wood, Steel, Aluminium and Fibreglass boats. When in doubt contact for advise.

Colors



Colore: VERDE CHIARO
Cod. Colore: 7K6015

Codice: 7K6015

Stripcarena

Listino

Formati Disponibili		Codice	Descrizione	Confezione
5L	0.75L	7K601500750	Stripcarena sverniciatore	0.75 lt
		7K601505000	Stripcarena sverniciatore	5.00 lt

SAFETY PRECAUTIONS

Before starting paint application attention should be paid to the symbols of risk specified on the label of each can. Please carefully read all the safety precautions advised on the label, or in the safety data sheet available on request at laboratorio@aemmecolori.it

NOTES

This information is provided to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, this information does not constitute any kind of implied warranties; in that sense the supplying company accepts from now responsibility that can be connected to an abnormal use of the products. The Engineering Department at your location is available for any questions related to the use of our products. The percentages of dilution and the drying time are to be considered only indicative, in relation to a temperature of 20 ° C and are therefore subject to change with the change of temperature, in the presence of particular weather conditions or application determining factors at the time of application.